



# AquataPoxy® A-61

## Technical Data Sheet

### MANUFACTURER

Raven Lining Systems  
13105 E. 61<sup>st</sup> Street, Suite A  
Broken Arrow, OK 74012  
(918) 615-0020

### DESCRIPTION

AquataPoxy® A-61 is a solvent-free, 100% solids, high build epoxy coating. Formulated for single coat applications (this product has no recoat window), A-61 is certified safe for cold potable water with a 5-hour cure time.

### PHYSICAL PROPERTIES (Typical)

Description	Method	Result
Tensile Strength	ASTM D 638	7,700 psi
Tensile Ultimate Elongation	ASTM D 638	1.2%
Compressive Strength	ASTM D 695	16,600 psi
Flexural Strength	ASTM D 790	10,600 psi
Hardness, Shore D	ASTM D 2240	88
Adhesion, Concrete	ASTM D 7234	Substrate Failure
Adhesion Steel (SSPC-SP 10)	ASTM D 4541	>2,500 psi
VOC's	Calculated	0.0 lbs/gal

### TYPICAL USES

Formulated for use on surfaces where corrosion and water resistance is needed, including:

- Water distribution and transmission lines 30" and larger
- Water tanks 50 gallons and larger
- Water treatment storage reservoirs
- Pharmaceutical and food facilities
- General maintenance

### COLOR

The standard Part A Resin is white; the Part B Curing Agent is green. When mixed the product is aqua. The Part B is also available in a translucent brown, when used with white Part A; the mixed product is a white color.

### FILM THICKNESS

AquataPoxy A-61 is a 100% solids epoxy with zero shrinkage. Wet film thickness and dry film thickness are the same (i.e. 40 mils WFT = 40 mils DFT). Depending on substrate type and profile, a maximum of 120 mils is recommended to prevent sagging. Typical recommended thickness for immersion duty is 25-80 mils on metal and 60-120 mils on concrete.

NSF/ANSI 61 maximum dry film thickness for pipes  $\geq$  30 inches or for tanks 200 gallons and larger: 120 mils.

### COVERAGE

Theoretical coverage is 40 square feet per gallon at 40 mils wet film thickness. Actual surface coverage will depend on substrate porosity and roughness. A wet film thickness gauge may be used to determine actual coating coverage.

### APPLICATION

Apply in a single coat with brush, roller, airless or air-assisted spray or other suitable method. Optimal proportioning and mixing is achieved with the use of a Raven Lining Systems approved plural component airless spray system. For best results, apply this product to concrete when its temperature is stable or falling. After the coating has set hard to touch it should be visually inspected. If applying multiple coats, abrade and clean the surface to remove debris, dust or other contaminants before applying the next coat.

### THINNING

**Do not thin with solvents.** If lower viscosity is needed, heat unmixed material by placing the containers in hot tap water until the desired flow properties are obtained. To heat larger quantities, drum heaters or inline heaters on specialized spray equipment may be used. Unmixed material should not be heated above 150°F.

### COMPONENTS AND MIX RATIO

Part A Resin: Part B Curing Agent mix ratio is 3:1 by volume.

### HAND MIXING

Individually mix both Part A and Part B containers prior to measuring out 3 parts of Part A to 1 part of Part B by volume into a clean disposable pail. Completely mix combined A & B for a minimum of one minute before transferring contents to a clean pail. Continue mixing at least another minute, scraping the sides and bottom, to obtain a thorough mix before application. Properly mixed material will be a uniform color without light or dark spots.

### CLEAN UP

To clean tools, use acetone, MEK or xylene. To clean skin, wash immediately and thoroughly with soap and water. Refer to the Material Safety Data Sheet for additional information on health and safety.

# AquataPoxy A-61

---

## POT LIFE

The pot life is 20 minutes for one gallon at 72°F. Longer pot life is possible by mixing smaller amounts and/or cooling down the part A & B before mixing.

## CURE TIME

Thin film set time varies with substrate temperature and application thickness. Generally, the coating will be tack-free in 3 hours at 72°F and dry-hard in about 4½ hours. This product is designed for single coat applications.

NSF/ANSI 61 cure time before service is 5 hours at 72°F.

*Potable Water Pipelines:* After 5 hours cure at 72°F, follow standard plumbing practices for clearing sand, debris or contaminants prior to service by flushing with 72°F potable water at 2½ to 3½ gallons per minute.

## SUBSTRATE TEMPERATURE

Minimum recommended substrate temperature: 50°F  
Maximum recommended substrate temperature: 120°F

## TEMPERATURE RESISTANCE

Maximum recommended dry temperature: 200°F. Wet temperature resistance depends on chemical concentration and exposure time.

## SURFACE PREPARATION

Prior to coating, the substrate must be prepared in a manner that provides a uniform, clean, sound, neutralized surface suitable for the specified coating. The substrate must be free of all contaminants, such as oil, grease, rust, scale or deposits. In general, coating performance is proportional to the degree of surface preparation.

*Steel* surfaces may require “Solvent Cleaning” (SSPC-SP 1) to remove oil, grease and other soluble contaminants. Chemical contaminants may be removed according to SSPC-SP 12/NACE No. 5. Identification of the contaminants along with their concentrations may be obtained from laboratory and field tests as described in SSPC-TU 4 “Field Methods for Retrieval and Analysis of Soluble Salts on Substrates”. Surfaces to be coated should then be prepared according to SSPC-SP 5/NACE No.1 “White Blast Cleaning” for immersion service or SSPC-SP 10/NACE No. 2 “Near White

Blast Cleaning” for all other service. In certain situations, an alternate procedure may be to use high (>5,000 psi) or ultrahigh (>10,000 psi) pressure water cleaning or water cleaning with sand injection. The resulting anchor profile shall be 2.5-5.0 mils and be relative to the coating thickness specified.

*Concrete and Masonry* surfaces must be sound and contaminant-free with a surface profile equivalent to a minimum CSP3 to CSP5 in accordance with ICRI Technical Guideline No. 310.2R-2013. This can generally be achieved by abrasive blasting, shot blasting, high pressure water cleaning, water jetting, or a combination of methods.

## AVAILABLE PACKAGES

Available in one gallon kits (3 quarts of part A in a gallon pail and a quart of part B), 5 gallon pails (20-gallon kit), 30 gallon drums (120-gallon kit) and 55 gallon drums (220-gallon kit). Kits are supplied in the correct proportions of A & B; these two components must be mixed together before use.

## SHELF LIFE AND STORAGE

Product shelf life is 1 year from purchase date in original unopened containers, stored in a sheltered area between 60°F and 80°F (15°C and 27°C).

## SAFETY

MSDS's are available on the website ([www.ravenlining.com](http://www.ravenlining.com)) or upon request. All personnel should read and understand the safety recommendations as set forth in the MSDS. Keep uncured product away from children at all times.

## CERTIFICATIONS

**Potable Water:** AquataPoxy A-61 is certified to the requirements of NSF/ANSI 61 - Drinking Water System Components by IAPMO R&T Inc.

**AWWA:** AquataPoxy A-61 meets the physical and performance requirements of ANSI/AWWA C 210, “Liquid Epoxy Coating Systems for the Interior and Exterior of Steel Water Pipelines”. AquataPoxy A-61 also meets the requirements of ANSI/AWWA D 102, section 4.4.4: Inside Coating System No. 3.

Warranty and Disclaimer: Raven Lining Systems, Inc. (“Raven”) warrants its products to be free of manufacturing defects in accord with applicable Raven quality control procedures and that they meet the formulation standards of Raven. To the best of our knowledge the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. If, within one year from purchase, any product is proven defective, Raven, at its sole option, will either replace the defective product or refund the purchase price. This warranty is void if the product is used contrary to Raven’s written directions.

**THE AFORESAID IS THE EXCLUSIVE WARRANTY AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. THERE IS NO WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE. UNDER NO CIRCUMSTANCES SHALL RAVEN BE LIABLE FOR INCIDENTAL OR CONSEQUENTIAL DAMAGES OR FOR LOST PROFITS. NO ACTION AGAINST RAVEN MAY BE COMMENCED MORE THAN ONE YEAR AFTER THE CLAIM ARISES.**